

DOUBLE-SKIN HONEYCOMB SUBSTRATE AND EXTRUSION DIE ASSEMBLY FOR MAKING THE SAME

Background of Invention

[0001] The invention relates generally to honeycomb substrates and particularly to a method of enhancing the isostatic strength of a honeycomb substrate having cells defined by thin webs.

[0002] Honeycomb substrates are widely used as catalyst carriers for purification of exhaust gases from internal combustion engines. A typical honeycomb substrate has a columnar body, the cross-sectional shape of which is typically round or oval. An array of parallel, straight channels is formed in the columnar body to allow passage of gases through the honeycomb substrate. The channels run axially along the length of the columnar body. The cross-section of the channels can be of any arbitrary shape, such as triangle, square, and hexagon. For automotive applications, the cross-section of the channels is frequently square because square channels are easier to manufacture. The channel walls may be coated with a porous washcoat containing an active catalyst. Alternatively, the active catalyst may be incorporated directly into the channel walls. In operation, exhaust gases flow into the channels and are converted into less noxious components in the presence of the active catalyst prior to exiting the honeycomb substrate. For illustration purposes, Figure 1 shows a cross-section of a typical prior-art honeycomb substrate **100** having an array of square cells (or channels) **102** defined by an array of square webs (or cell walls) **104** and bounded by a skin (or peripheral wall) **106**. Typically, the skin **106** has a circular or elliptical profile.

[0003] A honeycomb substrate is typically wrapped in a mat and inserted in a metal can prior to use in an automotive application. When the honeycomb substrate is inserted in a can, the forces required to restrain the honeycomb substrate within the can are uniformly distributed along the periphery of the honeycomb substrate, perpendicular to the skin of the honeycomb substrate. These forces have the greatest impact for the honeycomb substrate with square cells when applied at the 45° positions to the square webs, i.e., when applied in a direction along the diagonals of the square webs, as shown by the arrows in Figure 1. When loaded at this angle, the webs cannot function as columns under compression, and the honeycomb substrate is less rigid. In this state, the webs are subjected to high deflections,

which generate bending moments and undesirable tensile stresses in the honeycomb substrate. Typically, the honeycomb substrate is made of ceramic, a material that is inherently weak in tension. Hence, the tensile stress levels determine the strength of the canned ceramic honeycomb substrate.

[0004] In an effort to meet stringent automotive emission requirements, it has been necessary to reduce the thermal mass in the central region of the honeycomb substrate while increasing the geometric surface area and open frontal area of the honeycomb substrate. The thermal mass in the central region has been reduced and the geometric surface area has been increased by increasing the number of cells in the honeycomb substrate. At the same time, the thickness of the webs in the honeycomb substrate has been significantly reduced to increase the open frontal area of the honeycomb substrate and limit the back-pressure in the honeycomb substrate to an acceptable limit. Although reduction in web thickness has improved emissions performance, it has also resulted in marked reduction in the isostatic strength of the honeycomb substrate, making the honeycomb substrate more susceptible to damage during canning and lowering the thermal and mechanical durability of the honeycomb substrate in the application.

[0005] Various methods have been proposed for improving the isostatic strength of ceramic honeycomb substrates with thin webs. Some of these methods include increasing the cell density at a region near the periphery of the honeycomb substrate, thickening the webs at a region near the periphery of the honeycomb substrate, and using additives to strengthen the skin of the honeycomb substrate. One approach to increasing the cell density near the periphery of the honeycomb substrate involves subdividing the square cells near the periphery of the honeycomb substrate into smaller square cells or triangle cells. One method for increasing the thickness of the webs near the periphery of the honeycomb substrate includes rounding the square cells near the periphery of the honeycomb substrate. While these approaches can improve the isostatic strength of the honeycomb substrate, they can also yield undesirable results such as increase in pressure loss across the honeycomb substrate and/or reduction in thermal shock strength of the honeycomb substrate.

[0006] From the foregoing, there is desired a method of increasing the isostatic strength of a honeycomb substrate in all directions without adversely impacting the performance of the honeycomb substrate.

Summary of Invention

[0007] In one aspect, the invention relates to a honeycomb substrate which comprises an inner body having an inner skin and an array of inner webs defining an array of inner cells within the inner skin. The honeycomb substrate further comprises an outer body having an outer skin formed concentric with the inner skin and an array of outer webs defining an array of radially-oriented triangle cells between the inner skin and the outer skin. In one embodiment, the array of triangle cells comprises an array of radially-oriented diamond cells.

[0008] In another aspect, the invention relates to a honeycomb substrate which comprises an inner body having an inner skin and an array of inner webs defining an array of inner cells within the inner skin. The honeycomb substrate further comprises an outer body having an outer skin formed concentric with the inner skin and an array of outer webs defining an array of radially-oriented quadrilateral cells between the inner skin and the outer skin. The quadrilateral cells have a length along a circumferential direction that is no greater than a length of the inner cells.

[0009] In another aspect, the invention relates to a honeycomb substrate which comprises an inner body having an inner skin and an array of inner webs defining an array of inner cells within the inner skin. The honeycomb substrate further comprises an outer body having an outer skin formed concentric with the inner skin and an array of first outer webs arranged parallel to a diametrical axis of the inner body and an array of second outer webs arranged in a crisscross pattern. The first and second outer webs intersect to define an array of triangle cells between the inner skin and the outer skin.

[0010] In another aspect, the invention relates to an extrusion die assembly for making a double-skin honeycomb substrate which comprises an inner cell forming die having a central region and a peripheral region. The central region comprises an array of inner slots cut to define an array of inner pins and an array of central feedholes in communication with the array of inner slots. The peripheral region comprises an array of peripheral feedholes. The extrusion die assembly further includes a skin forming mask mounted coaxially with the inner cell forming die. The extrusion die assembly further includes at least one outer cell forming die mounted coaxially with and interposed between the inner cell forming die and the skin forming mask. The outer cell forming die has an array of outer slots cut to define an array of outer pins. The outer pins are spaced radially from the central region to define an inner skin slot and spaced radially from the skin forming mask to define an outer skin slot.

The inner skin slot is in selective communication with the array of peripheral feedholes. The outer skin slot is in selective communication with the peripheral feedholes through an opening in the outer cell forming die.

[0011] Other features and advantages of the invention will be apparent from the following description and the appended claims.

Brief Description of Drawings

[0012] Figure 1 is a cross-section of a prior-art honeycomb substrate having an array of square cells.

[0013] Figure 2A is a cross-section of a double-skin honeycomb substrate having a single layer of radially-oriented triangle cells formed between concentric skins at the periphery of the honeycomb substrate according to one embodiment of the invention.

[0014] Figure 2B is an enlargement of a section of the double-skin honeycomb substrate shown in Figure 2A.

[0015] Figure 3 is a cross-section of a double-skin honeycomb substrate having two layers of radially-oriented triangle cells formed between concentric skins at the periphery of the honeycomb substrate according to another embodiment of the invention.

[0016] Figure 4 is a graph showing relative comparison between radial displacement for a double-skin honeycomb substrate having a single layer of radially-oriented triangle cells formed between concentric skins and a double-skin honeycomb substrate having two layers of radially-oriented triangle cells formed between concentric skins in response to uniformly applied pressure.

[0017] Figure 5 is a cross-section of a double-skin honeycomb substrate having a single layer of radially-oriented diamond and triangle cells formed between concentric skins at the periphery of the honeycomb substrate according to another embodiment of the invention.

[0018] Figure 6A is a quarter cross-section of a double-skin honeycomb substrate having a single layer of radially-oriented quadrilateral cells formed between concentric skins at the periphery of the honeycomb substrate according to another embodiment of the invention.

[0019] Figure 6B shows fillets formed at junctions of the webs and outer skin of the double-skin honeycomb substrate shown in Figure 6A.

[0020] Figure 7A is a cross-section of a double-skin honeycomb substrate having triangle cells formed by crisscrossed and straight webs between concentric skins at the periphery of the substrate according to another embodiment of the invention.

[0021] Figure 7B shows the triangle cell structure of Figure 7A rotated 45° about the center of the honeycomb substrate.

[0022] Figure 8A is a top view of an extrusion die assembly for forming a double-skin honeycomb substrate with a single layer of cells arranged between concentric skins according to one embodiment of the invention.

[0023] Figure 8B is a cross-section of the extrusion die assembly shown in Figure 8A.

[0024] Figure 8C is a plan view of the outer cell forming die included in the extrusion die assembly of Figure 8A.

[0025] Figure 8D is a cross-section of the extrusion die assembly of Figure 8A according to another embodiment of the invention.

[0026] Figure 8E is a partial cross-section of an extrusion die assembly for forming a double-skin honeycomb substrate with two layers of cells arranged between concentric skins according to another embodiment of the invention.

[0027] Figure 8F is a partial cross-section of an extrusion die assembly according to another embodiment of the invention showing an alternate means of supplying batch material to an inner skin reservoir and an outer skin reservoir.

Detailed Description of Preferred Embodiments

[0028] The invention will now be described in detail with reference to a few preferred embodiments, as illustrated in the accompanying drawings. In the following description, numerous specific details are set forth in order to provide a thorough understanding of the invention. It will be apparent, however, to one skilled in the art, that the invention may be practiced without some or all of these specific details. In other instances, well-known features and/or process steps have not been described in detail in order to not unnecessarily obscure the invention. The features and advantages of the invention may be better understood with reference to the drawings and discussions that follow.

[0029] While not wishing to be bound by theory, the inventors believe herein that the isostatic strength of a honeycomb substrate can be enhanced by incorporating reinforcing webs near the periphery of the honeycomb substrate. The inventors propose a double-skin

structure whereby the reinforcing webs are arranged between at least two concentric skins near the periphery of the honeycomb substrate and are separated from the central region of the honeycomb substrate by the concentric skins. This allows the central region, which contains the main flow channels, to be optimized independently of the reinforcing webs to achieve a desired performance for a target application. The geometry and orientation of the reinforcing webs can be selected to achieve desired isostatic strength without significantly impacting the performance of the honeycomb substrate. The inventors believe herein that the geometry and orientation of the reinforcing webs are important to achieving enhanced isostatic strength in all directions along the periphery of the honeycomb substrate.

[0030] For illustration purposes, Figure 2A shows a double-skin honeycomb substrate **200** according to one embodiment of the invention. The double-skin honeycomb substrate **200** includes an inner honeycomb body **202** and an outer honeycomb body **204**. The inner and outer honeycomb bodies **202**, **204** are columnar and are typically made of a ceramic material, such as cordierite, but could also be made of other extrudable materials, such as glass, glass-ceramics, and plastic. The structure of the inner honeycomb body **202** may be optimized for a specific application, such as an automotive emissions application. The structure of the outer honeycomb body **204** is preferably designed to enhance the isostatic strength of the honeycomb substrate **200** in all directions along the periphery of the substrate. The structure of the outer honeycomb body **204** can be optimized independently of the structure of the inner honeycomb body **204**. This means that the isostatic strength of the honeycomb substrate **200** can be enhanced without significantly impacting the performance of the honeycomb substrate **200**, which would typically depend primarily on the structure of the inner honeycomb body **202**.

[0031] The inner honeycomb body **202** has an array of (inner) cells **206** defined by an array of (inner) webs **208** and an (inner) skin **210**. The cross-sectional shape of the honeycomb body **202** can be round, oval, or other appropriate shape for the target application. The cross-section of the inner cells **206** can be of any arbitrary shape, such as triangle, square, and hexagon. In the illustration, the cross-section of the inner cells **206** is shown as square. As previously mentioned, a square geometry is frequently used in automotive exhaust gas purification systems. Further, the invention provides significant advantages in terms of strength enhancement when used with a square geometry. The inner skin **210** has a circular profile in the illustration. In alternate embodiments, the inner skin **210**

may have an elliptical or other profile appropriate for the target application. The dimensions of the inner cells **206** and inner webs **208** can be selected to achieve a desired emissions performance or can be optimized for other applications. The invention provides advantages in terms of strength enhancement when the inner webs **208** are very thin, e.g., less than or equal to 0.15 mm in thickness.

[0032] The outer honeycomb body **204** includes an (outer) skin **212** formed concentric with the inner skin **210** and a layer of (outer) cells **214** defined by (outer) webs **216**. The outer webs **216** form a bridge between the inner skin **210** and the outer skin **212**. The outer cells **214** have a triangle cross-section. The term “triangle” is intended to cover triangular-like shapes where one or more sides of the triangle have a curvature and/or one or more corners of the triangle include fillets. The triangle could be isosceles, including equilateral, or scalene, or right-angle. The outer cells **214** are radially-oriented with respect to the center of the inner honeycomb body **202**. The term “radially-oriented” means that a major dimension of the outer cell **214** lies along a radial line drawn outwardly from the center of the inner honeycomb body **202**. For a triangle cell, this major dimension could be the altitude of the cell. As illustrated in Figure 2B, a radial line **218** drawn from the center of the inner honeycomb body **202** to the vertex **220** of a triangle cell **214** perpendicularly intersects the side (or base) **222** of the triangle cell **214** opposite the vertex **220** of the triangle cell **214**.

[0033] Returning to Figure 2A, the outer cells **214** are uniformly distributed along the inner and outer skins **210**, **212** so that a load applied perpendicularly to the outer skin **212** is uniformly distributed to the inner skin **210** via the outer webs **216**. When a load is applied to the outer skin **212**, the outer webs **216** act as columns under compression, which makes the honeycomb substrate **200** very rigid. In one embodiment, the geometry of the outer webs **216** is selected such that the applied load does not result in high deflections that can generate bending moments and undesirable tensile stresses in the honeycomb substrate **200**. In particular, the outer webs **216** act to reduce the loads at the 45° positions of the inner honeycomb body **202** where, for a square cell matrix, the tensile loads and, consequently, the probability of failure are highest.

[0034] In general, design of the outer honeycomb body **204** would depend on the target application and the desired isostatic strength. The geometric variables may include density of the outer cells **214**, geometry of the outer cells **214**, thickness of the outer webs **216**, number of layers of outer cells **214** formed between the inner and outer skins **210**, **212**,

gradations in outer cell density and/or outer web thickness, thickness of the inner and outer skins **210**, **212** as well as any intermediate skin formed between stacked layers of outer webs. These geometric variables can be selected to give an appropriate balance between isostatic strength, thermal mass, and chip resistance. For uniform flow, the dimensions of the outer cells **214** can be selected such that the outer cells **214** have equivalent hydraulic diameter to the inner cells **206**. Fillets (not shown) may be formed at the intersections between the outer webs **216** and the outer skin **212**. Concave fillets are desirable for reducing stress concentration. However, convex fillets may also be used to improve adherence of the outer webs **216** to the outer skin **212**. In one embodiment, the radius of the fillets could range from 0.05 to 0.2 mm, depending on the dimensions of the outer webs and outer skin. The following design constraints have been found to provide desirable results under a uniform pressure loading of 1 MPa:

$$0.1 \cdot L1 \leq L3 \leq 2 \cdot L1 \quad (1)$$

and/or

$$t2 \geq 0.5 \cdot t1 \quad (2)$$

where, as illustrated in Figure 2B, $L1$ is the length of the square cell **206**, $L3$ is the length (or altitude) of the triangle cell **214** in the radial direction, $t1$ is the thickness of the square web **208**, and $t2$ is the thickness of the triangle web **216**.

[0035] Figure 3 shows a quarter cross-section of a double-skin honeycomb substrate **300** according to another embodiment of the invention. The honeycomb substrate **300** includes an inner honeycomb body **302** and an outer honeycomb body **304**. In one embodiment, the inner honeycomb body **302** includes square cells **306** defined by square webs **308** and bounded by an inner skin **310**. The outer honeycomb body **304** includes an outer skin **312** and two layers of triangle cells **314**, **316** formed between the inner skin **310** and outer skin **312**. The triangle cells **314** are defined by triangle webs **318**, and the triangle cells **316** are defined by triangle webs **320**. An intermediate skin **322** is formed between the layers of triangle cells **314** and **316**. The intermediate skin **322** is concentric with the inner skin **310** and the outer skin **312**. The triangle cells **314**, **316** are radially oriented with respect to the center of the inner honeycomb body **302**. Further, the triangle cells **314**, **316** are uniformly distributed along the periphery of the inner honeycomb body **302** so that a load applied perpendicular to the outer skin **312** is uniformly distributed to the inner skin **310** and the inner square webs **308** via the outer triangle webs **318**, **320** and intermediate skin **322**.

[0036] The sizes and thicknesses of the triangle cells **314**, **316** and triangle webs **318**, **320** can be selected to provide the desired isostatic strength. As an example, desirable results have been achieved under a uniform pressure loading of 1 MPa when the lengths (or altitudes) of the triangle cells **314**, **316** along the radial direction are in a range from 0.1 to 2 times the length of the square cell **306** and/or when the thicknesses of the triangle webs **318**, **320** are in a range from 0.1 to 4 times the thickness of the square web **308**. It should be noted that the geometry of the triangle webs **320** and cells **316** can be different from or the same as the geometry of the triangle webs **318** and cells **314**. Further, the outer honeycomb body **304** can have more than two layers of triangle cells/webs. Further, the thicknesses of the interface skin **322** and outer skin **312** can be varied as necessary to achieve desired balance between isostatic strength, thermal mass, and chip resistance. Further, the intersections between the triangle webs **320** and the outer skin **312** can be filleted to either reduce stress concentration at the intersections or improve adherence of the triangle webs to the outer skin. In one embodiment, the radius of the fillets could range from 0.05 to 0.2 mm, depending on the dimensions of the triangle webs and the outer skin.

[0037] A honeycomb substrate structure having a double layer of triangle cells/webs (shown in Figure 3) is expected to have higher isostatic strength than a honeycomb substrate having a single layer of triangle cells/webs (shown in Figures 2A and 2B). In general, the higher the number of layers of triangle cells/webs incorporated at the periphery of the honeycomb substrate, the better the isostatic strength of the honeycomb substrate. Figure 4 compares the relative radial displacement of the outer skin of the outer honeycomb body under 1-MPa uniform pressure loading for a single layer of triangle cells/webs and a double layer of triangle cells/webs. Figure 4 shows that the double layer of triangle cells/webs can better absorb radial displacement than the single layer of triangle cells/webs, distributing the applied load to the elastic matrix cells. The results show that a double layer of triangle cells can lower radial displacement by about 15% in comparison to a single layer of triangle cells/webs.

[0038] Figure 5 shows a quarter cross-section of a double-skin honeycomb substrate **500** according to another embodiment of the invention. The honeycomb substrate includes an inner honeycomb body **502** and an outer honeycomb body **504**. In one embodiment, the inner honeycomb body **502** includes inner square cells **506** defined by inner square webs **508** and an inner skin **510**. The outer honeycomb body **504** includes an outer skin **512** and outer

diamond cells **514** and triangle cells **515** defined by outer diamond webs **516**. The diamond cells **514** and triangle cells **515** are radially oriented with respect to the center of the inner monolith body **502**. In the case of the diamond cell **514**, a radial line **518** drawn from the center of the inner honeycomb body **504** through a diamond cell **514** would pass through opposite vertices of the diamond cell **514**. It should be noted that the term “diamond” is intended to encompass diamond-like shapes in which the four sides of the diamond are not equal. For ease of manufacturing, it is desirable that each side of the diamond cell is generally parallel to a side of an adjacent triangle cell. The single layer of diamond and triangle cells **514**, **515** and diamond webs **516** offer a benefit similar to the double layer of triangle cells/webs shown in Figure 3. Further, the diamond and triangle cell structure may be easier to manufacture since it does not require the intermediate skin (**322** in Figure 3) used with the double layer of triangle cells/webs. The angles and thicknesses of the diamond webs **516** can be selected to achieve the desired isostatic strength. Further, two or more layers of diamond and triangle cells **514**, **515** can be used to further enhance the isostatic strength of the honeycomb substrate. The intersections between the diamond webs **516** and the outer skin **512** can be filleted to either reduce stress concentration at the intersections or improve adherence of the diamond webs to the outer skin. In one embodiment, the radius of the fillets could range from 0.05 to 0.2 mm, depending on the dimensions of the diamond webs and the outer skin.

[0039] Figure 6A shows a quarter cross-section of a honeycomb substrate **600** according to another embodiment of the invention. The honeycomb substrate **600** includes an inner honeycomb body **602** and an outer honeycomb body **604**. In one embodiment, the inner honeycomb body **602** includes square cells **606** defined by square webs **608** and bounded by an inner skin **610**. The outer honeycomb body **604** includes an outer skin **612** and quadrilateral cells **614** defined by straight webs **616**. The quadrilateral cells **614** are radially oriented with respect to the center of the inner monolith body **602**, i.e., a radial line **618** drawn from the center of the inner monolith body **602** through a quadrilateral cell **614** perpendicularly bisects opposite sides of the quadrilateral cell **614**. The term “quadrilateral” is intended to encompass shapes where one or more sides of the quadrilateral have a curvature, such as shown in Figure 6A.

[0040] The geometry and spacing of the quadrilateral cells **614** and straight webs **616** can be selected to provide the desired isostatic strength. The following conditions have been found to provide desirable results under a uniform pressure loading of 1 MPa:

$$0.5 \cdot L1 \leq L2 \leq L1 \quad (3)$$

$$0.1 \cdot L1 \leq L3 \leq 2 \cdot L1 \quad (4)$$

$$t3 \geq t1 \quad (5)$$

$$t4 \geq 2 \cdot t1 \quad (6)$$

$$t3 > 0.25 \cdot t2 \quad (7)$$

$$t4 > t2 \quad (8)$$

where L1 is the length of the square cell **606**, L2 is the length of the quadrilateral cell **614** along the circumferential direction of the substrate, L3 is the length of the quadrilateral cell **614** along the radial direction of the substrate, t1 is the thickness of the square cell **606**, t2 is the thickness of the straight web **616**, t3 is the thickness of the inner skin **610**, t4 is the thickness of the outer skin **612**.

[0041] In a manner similar to the one described for the other embodiments, more than a single layer of quadrilateral cells **614** satisfying the conditions above can be formed between the inner and outer skins **610**, **612**. Referring to Figure 6B, concave fillets **620** are formed at the intersections between the straight webs **616** and the outer skin **612** to reduce stress concentration at these intersections. The fillets **620** are shown at only a few intersections for illustration purposes. In general, a portion or all of the intersections may be filleted. Further, some or all of the concave fillets **620** may be replaced with convex fillets to improve adherence of the straight webs **616** to the outer skin **612**. In one embodiment, the radius of the fillets **620** could range from 0.05 to 0.2 mm for a double-skin honeycomb substrate satisfying equations (3) through (8).

[0042] Table 1 below shows radial displacement for four examples (Wagon-1 through Wagon-4) of the double-skin honeycomb substrate structure shown in Figure 6A under a uniform pressure of 1 MPa.

Table 1

Design	Geometric Variables	Radial Displacement (μm) of Outer Skin $30^\circ - 60^\circ$ Orientation (Approximation by Averaging)
Square (Reference)	600 cells, $t_1 = 0.15 \text{ mm}$, $L_1 = 1 \text{ mm}$	4.97
Wagon-1	$L_2/L_1 = 0.95$, $L_3/L_1 = 1.15$ $t_2 = t_3 = t_4 = 2t_1$	4.87
Wagon-2	$L_2/L_1 = 0.95$, $L_3/L_1 = 0.725$ $t_2 = t_3 = t_4 = 2t_1$	4.78
Wagon-3	$L_2/L_1 = 0.5$, $L_3/L_1 = 1.15$ $t_2 = t_3 = t_4 = 2t_1$	4.70
Wagon-4	$L_2/L_1 = 0.5$, $L_3/L_1 = 0.5$ $t_2=t_4=t_1$, $t_3=1.25t_1$	4.81

[0043] Figure 7A shows a cross-section of a honeycomb substrate 700 according to another embodiment of the invention. The honeycomb substrate includes an inner honeycomb body 702 and an outer honeycomb body 704. In one embodiment, the inner honeycomb body 702 includes inner square cells 706 defined by inner square webs 708 and bounded by an inner skin 710. The outer honeycomb body 704 includes outer triangle cells 714. The outer triangle cells 714 are formed by a first set of outer webs 716, which are parallel to a diametrical axis x of the substrate 700, and a second set of outer webs 718, which are arranged in a crisscross pattern. The diametrical axis x is perpendicular to a side of the square cell 706. The webs 716, 718 intersect to form the triangle cells 714. The triangle cells 714 are concentric with the inner honeycomb body 702 but do not exhibit the radial orientation described for the other embodiments. The density of the triangle cells 714 and the geometry of the webs 716, 718 and angle of intersection of the webs 716, 718 can be selected to achieve desired isostatic strength for the honeycomb substrate.

[0044] The outer honeycomb body 704 can be rotated 45° , as shown in Figure 7B, to strengthen the weakest spots in the inner square structure. One or more layers of the triangle cells 714 can be used to further enhance the isostatic strength of the honeycomb substrate. In

one embodiment, the thickness of the webs **716**, **718** is greater than 0.5 times the thickness of the square web **708**, and a length (or altitude) of the triangle cell **714** is less than 2 times a length of the square cell **706**.

[0045] Figure 8A shows a plan view of an extrusion die assembly **800** according to an embodiment of the invention. The extrusion die assembly **800** can be used to make a double-skin honeycomb substrate having an array of inner cells defined by an array of inner webs and an array of outer cells defined by an array of outer webs, wherein the inner cells and webs are bounded by an inner skin and the outer cells and webs are bounded by the inner skin and an outer skin, wherein the outer skin is concentric with the inner skin. The extrusion die assembly **800** includes an inner cell forming die **802**, an outer cell forming die **804**, and a skin forming mask **806**. The inner cell forming die **802** is used to form the inner webs that define the inner cells. The inner cell forming die **802** and the outer cell forming die **804** cooperate to define the shape and thickness of the inner skin. The outer cell forming die **804** is used to form the outer webs that define the outer cells. The outer cell forming die **804** and the skin forming mask **806** cooperate to define the shape and thickness of the outer skin. A single outer cell forming die **804** can be used to form a single layer of outer cells between the inner skin and the outer skin or, as will be described later, multiple outer cell forming dies can be used to form multiple layers of outer cells between the inner skin and the outer skin of the honeycomb substrate.

[0046] Figure 8B shows a vertical cross-section of the extrusion die assembly **800**. In this figure, the inner cell forming die **802** has a central region **808**. An array of (inner) slots **812** is cut in the central region **808** to define an array of (inner) pins **810**. In operation, batch material is extruded through the inner slots **812** to form the inner webs of the honeycomb substrate. In one embodiment, the transverse cross-section of the inner pins **810** is square (see Figure 8A). In general, the transverse cross-section of the inner pins **810** can be any shape common to honeycomb structures, e.g., triangle and hexagon. The central region **808** of the inner cell forming die **802** further includes an array of (inner) feedholes **814**, which extend from an inlet face **815** of the die to the array of inner slots **812**. The inner feedholes **814** supply batch material to the inner slots **812**. The size and location of the inner feedholes **814** relative to the inner slots **812** are selected to achieve desired rate of flow through the inner slots **812**. As an example, an inner feedhole **814** may correspond to each or every other inner slot **812** or may correspond to each or every other intersection of the slots **812**.

[0047] The inner cell forming die **802** also includes a peripheral region **822** formed contiguous with the central region **808**. The peripheral region **822** provides a mounting surface **820** for the outer cell forming die **802** and includes feedholes **828** for feeding batch material to spaces around and in the outer cell forming die **804**. The outer cell forming die **804** includes an annular body **816** which terminates in an annular flange **818**. The annular flange **818** is mounted on the mounting surface **820** provided by the peripheral region **822**. In one embodiment, a shim **824** is interposed between the mounting surface **820** and the annular flange **818** to define an inner skin reservoir **826** between the peripheral region **822** and the annular flange **818**. The feedholes **828** in the peripheral region **822** supply batch material to the inner skin reservoir **826**. The annular body **816** is radially spaced from the central region **808** to define an inner skin slot **825**, and the inner skin slot **825** is in communication with the inner skin reservoir **826**. Batch material is extruded through the inner skin slot **825** to form the inner skin of the honeycomb substrate.

[0048] Referring to Figure 8C, an array of (outer) slots **832** is cut in the annular body **816** to form a plurality of (outer) pins **830**. Batch material fills the outer slots **832** to form the outer webs of the honeycomb substrate. In one embodiment, the outer pins **830** are radially-oriented with respect to the center of the inner cell forming die (**802** in Figure 8A) so as to allow radially-oriented cells to be formed between the inner and outer skins of the honeycomb substrate. The transverse cross-section of the outer pins **830** may be quadrilateral, such as shown in the figure, or may have other shape, such as triangle or diamond. Returning to Figure 8B, the upper end of the outer pins **830** may be flush with the upper end of the inner cell forming die **802** or may be extended partly or all the way up to the top of the skin forming mask **806**, as indicated by the dotted line **835**.

[0049] The skin forming mask **806** is mounted on a mounting surface **834** provided by the annular flange **818** of the outer cell forming die **804**. In one embodiment, a shim **836** is interposed between the outer cell forming die **804** and the skin forming mask **806** to define an outer skin reservoir **838**. In one embodiment, the annular flange **818** includes a plurality of orifices **840** (see also Figure 8C) which provide communication between the inner skin reservoir **826** and the outer skin reservoir **838**. The orifices **840** could be holes or slots. The orifices **840** may provide a normal or an emergency flow path between the inner and outer skin reservoirs **826**, **838**. In the alternate embodiment shown in Figure 8D, one or more of the outer slots **832** in the annular body **816** are extended radially to the annular flange **818**

area to provide a flow path between the inner skin reservoir **826** and the outer skin reservoir **838**. Returning to Figure 8B, the skin forming mask **806** is radially spaced from the annular body **816** to define an outer skin slot **842**, which is in communication with the outer skin reservoir **838** and the outer slots **832**. Batch material is extruded through the outer skin slot **842** to form the outer skin of the honeycomb substrate.

[0050] In one embodiment, two flow paths are defined between the inner skin reservoir **826** and the outer slots **832**: one flow path runs from the inner skin reservoir **826** to the inner skin slot **825** to the outer slots **832**, and the other flow path runs from the inner skin reservoir **826** through the orifices **840** in the annular flange **816** to the outer skin reservoir **838** to the outer skin slot **842** to the outer slots **832**. Either or both of these flow paths can be used to supply extrudable material to the outer slots **832**. Preferably, the flow velocity in the outer slots **832** increases gradually from the inner skin slot **825** to the outer skin slot **842**. The width of the outer skin slot **842** can be selected to be different from that of the inner skin slot **825** such that flow from the outer skin slot **842** into the outer slots **832** is restricted relative to flow from the inner skin slot **825** into the outer slots **832**. The flow characteristics in the inner and outer skin reservoirs **826**, **838** can also be controlled to achieve desired flow velocities in the inner and outer skin slots **825**, **842** which will result in the desired flow profile in the outer slots **832**.

[0051] In operation, batch material is fed into the feedholes **814**, **828** in the inner cell forming die **802**. The batch material is extruded through the inner slots **812**, the inner skin slot **825**, the outer slots **832**, and the outer skin slot **842**. The extruded structure exits the extrusion die assembly **800** through the annular opening **844** in the skin forming mask **806**. The volume of the batch material in the inner skin reservoir **826** is dependent on the extent of the radial overhang of the annular flange **818** over the inner skin reservoir **826**, and the volume of the batch material in the outer skin reservoir **838** is dependent on the extent of the radial overhang of the skin forming mask **806** over the outer skin reservoir. The rate of flow of the batch material through the feedholes **828** and the orifices **840** and the volume of the inner and outer skin reservoirs **826**, **838** determine the character of the inner skin, outer webs, and outer skin of the honeycomb substrate. The rate of flow of batch material through the feedholes **814** feeding the inner slots **812** may be controlled independently of the rate of flow of batch material through the feedholes **828** feeding the inner skin slot **825**, the outer slots **832**, and the outer skin slot **842**.

[0052] Figure 8E shows the extrusion die assembly **800** modified to form a honeycomb substrate having two layers of outer cells between the inner skin and the outer skin. The modification includes interposing a second outer cell forming die **850** between the outer cell forming die **804** and the skin forming mask **806**. The second outer cell forming die **850** is axially spaced from the first outer cell forming die **804** by a shim **852**. An intermediate skin reservoir **854** is defined between the first and second outer cell forming dies **804, 850** and the shim **852**. The second outer cell forming die **850** is radially spaced from the outer cell forming die **804** to form an intermediate skin slot **856**, which is in communication with the intermediate skin reservoir **854**, which is in communication with the inner skin reservoir **826** through the orifices **840** in the outer cell forming die **804**. The outer skin slot **842** is now defined between the second outer skin forming die **850** and the skin forming mask **806**. The second outer skin forming die **850** include orifices **858** which allow communication between the intermediate skin reservoir **854** and the outer skin reservoir **838**. The second outer cell forming die **850** includes slots **860** for forming the second layer of outer cells. The intermediate skin slot **856** is used in forming the intermediate skin that separates the first layer of outer cells formed by the outer cell forming die **804** from the second layer of outer cells formed by the second outer cell forming die **850**. More than two outer cell forming dies may be interposed between the inner cell forming die **802** and the skin forming mask **806** to form more than two layers of cells between the inner skin and the outer skin of the honeycomb substrate.

[0053] Other modifications that can be made to the extrusion die assembly **800** include changing the flow path of batch material from the feedholes in the peripheral region to the inner skin slot, outer slots, and outer skin slot. For example, Figure 8F shows the peripheral region **822** modified to include an array of peripheral pins **862**, which define an array of peripheral slots **864**. The peripheral region **822** includes a first set of feedholes **866** in communication with the peripheral slots **864**. The peripheral region **822** also includes a second set of feedholes **868** which open to the mounting surface **820** for the outer cell forming die **804**. The inner skin reservoir **826** is defined between the portion of the peripheral region **822** containing the peripheral slots **864** and the corresponding portion of the outer cell forming die **804**. The inner skin reservoir **826** is in communication with the first set of feedholes **866** through the peripheral slots **864**. The second set of feedholes **868** are in direct communication with the orifices **840** in the annular flange **818** of the outer cell forming

die **804**. The orifices **840** are in turn in communication with the outer skin reservoir **838**. This arrangement allows independent control of the flow of batch material into the inner and outer skin reservoirs **826**, **838**. If desired, a shim reservoir may be formed between the second set of feedholes **868** and the orifices **840** in the annular flange **818**.

[0054] The extrusion die assembly described above can be manufactured using existing methods for making extrusion dies. The inner cell forming die can be made by machining holes in a lower portion of a block that is made of a machinable material. These holes would serve as feedholes. A process such as wire electrical discharge machining (EDM) can be used to cut the extrusion slots in the upper portion of the block. Pins remain on the upper portion of the block after the slots are cut. The pins at the periphery of the block can be shortened or completely removed. The outer cell forming die can be made in a similar manner. The extrusion slots made in the outer cell forming die could have any of the geometries described in conjunction with the double-skin honeycomb substrates above or may have other geometries.

[0055] The invention provides one or more advantages. The invention provides reinforcing structures near the periphery of the honeycomb substrate that have a geometry and orientation such that the isostatic strength of the honeycomb substrate is enhanced. The reinforcing structures are separated from the inner structure of the honeycomb substrate, making it possible to optimize the geometry of the reinforcing structures without significantly perturbing the inner structure of the honeycomb substrate. In this way, the inner structure of the honeycomb substrate can be optimized to achieve a desired performance, while the reinforcing structures can be designed to provide the desired isostatic strength.

[0056] While the invention has been described with respect to a limited number of embodiments, those skilled in the art, having benefit of this disclosure, will appreciate that other embodiments can be devised which do not depart from the scope of the invention as disclosed herein. Accordingly, the scope of the invention should be limited only by the attached claims.